



BEST AVAILABLE COPY

Attorney's Docket: 2002DE130
 Serial No.: 10/656,313
 Group: 1713

Amendments to the Claims

1. (Currently Amended) A pulverulent flame-retardant composition with low dust level, comprising an organophosphorus flame retardant component, and at least one dust-reduction additive, wherein the at least one dust reduction additive is non-aqueous.

2. (Previously Presented) The pulverulent flame-retardant composition with low dust level, as claimed in claim 1, wherein the organophosphorus flame-retardant component is selected from the group consisting of a phosphinic salt of the formula (I) a diphosphinic salt of the formula (II), a polymer of formula (I), a polymer of formula (II), and a mixture of polymers of formula (I) and (II),



where

R^1 and R^2 are identical or different and are C_1 - C_6 -alkyl, linear or branched, or aryl;

R^3 is C_1 - C_{10} -alkylene, linear or branched, C_6 - C_{10} -arylene, -alkylarylene, or -arylalkylene;

BEST AVAILABLE COPY

Attorney's Docket: 2002DE130
Serial No.: 10/656,313
Group: 1713

M is Mg, Ca, Al, Sb, Sn, Ge, Ti, Zn, Fe, Zr, Ce, Bi, Sr, Mn, Li, Na, K, and
a protonated nitrogen base;

m is from 1 to 4;

n is from 1 to 4;

x is from 1 to 4.

3. (Previously Presented) The pulverulent flame-retardant composition with low
dust level, as claimed in claim 1, wherein M is calcium, aluminum or zinc.

4. (Previously Presented) The pulverulent flame-retardant composition with low
dust level, as claimed in claim 1, wherein R¹ and R² are identical or different and are
C₁-C₆-alkyl, linear or branched, or phenyl.

5. (Previously Presented) The pulverulent flame-retardant composition with low
dust level, as claimed in claim 1, wherein R¹ and R² are identical or different, and are
methyl, ethyl, n-propyl, isopropyl, n-butyl, tert-butyl, n-pentyl, or phenyl.

6. through 16. (Cancelled)

17. (Previously Presented) The pulverulent flame-retardant composition with low
dust level, as claimed in claim 1, wherein the dust-reduction additive comprises
alkylalkoxylates having from 8 to 22 carbon atoms and from 1 to 80 EO units per
mole of alcohol.

18. through 20. (Cancelled)

21. (Previously Presented) The pulverulent flame-retardant composition with low
dust level, as claimed in claim 1, which has a median particle size of from 0.1 to
1 000 μm .

BEST AVAILABLE COPY

Attorney's Docket: 2002DE130
Serial No.: 10/656,313
Group: 1713

22. (Previously Presented) The pulverulent flame-retardant composition with low dust level, as claimed in claim 1, having an average bulk density of from 80 to 800 g/l.

23. (Currently Amended) The pulverulent flame-retardant composition with low dust level, as claimed in claim 1, wherein the ratio of amount of dust-reduction additive to that of organophosphorus flame-retardant component is from ~~4:999~~ 1:99 to 1:4.

24. through 39. (Cancelled)

40. (Previously Presented) The pulverulent flame-retardant composition with low dust level as claimed in claim 1, which has a median particle size of from 1 to 100µm.

41. (Currently Amended) The pulverulent flame-retardant composition with low dust level as claimed in claim 1, having an average ~~bulk~~ bulk density of from 200 to 700g/l.

42. (Previously Presented) The pulverulent flame-retardant composition with low dust level, as claimed in claim 1, wherein the ratio of amount of dust-reduction additive to that of organophosphorus flame-retardant component is from 1:99 to 1:19.